

• B6000 •
• P6058 • P6808 •
SIDE CURTAINS

PANAMA



Fabric		100% PES 1100 dtex	
Weight		900 g/m ²	DIN EN ISO 2286-2
Lacquering		1/1	
Embossing		Glossy	
Breaking strength	Warp	4000 N/5cm	EN ISO 1421-1
	Weft	4000 N/5cm	
Tear strength	Warp	600 N	DIN 53 363
	Weft	500 N	
Adhesion		100 N/5cm	EN ISO 2411
Temperature resistance		-30/+70°C	DIN EN 1876-2
Light fastness	(except white and (half-) transparent)	7-8	ISO 105 B02
Fire behavior		<100 mm/min	ISO 3795
Application		Truck/ Side curtains	

S=STANDARD - NS=This is not a standard product. Only on request. Minimum 1.000LM

COLOR	RAL	WIDTH (cm)	
		285	300
1001	-	<input type="checkbox"/>	<input type="checkbox"/> S
1003	1014	<input type="checkbox"/>	<input type="checkbox"/> S
1018	1018	<input type="checkbox"/>	<input type="checkbox"/> S
1021	1021	<input type="checkbox"/>	<input type="checkbox"/> S
1024	1003	<input type="checkbox"/>	<input type="checkbox"/> S
1025	-	<input type="checkbox"/>	<input type="checkbox"/> S
1059	1032	<input type="checkbox"/>	<input type="checkbox"/> S
1622	-	<input type="checkbox"/>	<input type="checkbox"/> S
1623	-	<input type="checkbox"/>	<input type="checkbox"/> S
3001	-	<input type="checkbox"/>	<input type="checkbox"/> S
3002	-	<input type="checkbox"/>	<input type="checkbox"/> S
3015	3002	<input type="checkbox"/>	<input type="checkbox"/> S
3016	-	<input type="checkbox"/>	<input type="checkbox"/> S
3017	-	<input type="checkbox"/>	<input type="checkbox"/> S
3018	-	<input type="checkbox"/>	<input type="checkbox"/> S
3021	2008	<input type="checkbox"/>	<input type="checkbox"/> S
3056	-	<input type="checkbox"/>	<input type="checkbox"/> S
3057	4007	<input type="checkbox"/>	<input type="checkbox"/> S
3105	-	<input type="checkbox"/>	<input type="checkbox"/> S
5001	-	<input type="checkbox"/>	<input type="checkbox"/> S
5003	5012	<input type="checkbox"/>	<input type="checkbox"/> S
5004	5013	<input type="checkbox"/>	<input type="checkbox"/> S
5007	-	<input type="checkbox"/>	<input type="checkbox"/> S
5020	-	<input type="checkbox"/>	<input type="checkbox"/> S
5023	-	<input type="checkbox"/>	<input type="checkbox"/> S
5025	-	<input type="checkbox"/>	<input type="checkbox"/> S
5026	-	<input type="checkbox"/>	<input type="checkbox"/> S
5027	-	<input type="checkbox"/>	<input type="checkbox"/> S
5028	-	<input type="checkbox"/>	<input type="checkbox"/> S
5029	-	<input type="checkbox"/>	<input type="checkbox"/> S
5030	-	<input type="checkbox"/>	<input type="checkbox"/> S
5031	5010	<input type="checkbox"/>	<input type="checkbox"/> S
5032	-	<input type="checkbox"/>	<input type="checkbox"/> S
(New) 5033	-	<input type="checkbox"/>	<input type="checkbox"/> S
5061	-	<input type="checkbox"/>	<input type="checkbox"/> S
5063	5002	<input type="checkbox"/>	<input type="checkbox"/> S
5104	5011	<input type="checkbox"/>	<input type="checkbox"/> S
(New) 5158	-	<input type="checkbox"/>	<input type="checkbox"/> S
6001	-	<input type="checkbox"/>	<input type="checkbox"/> S
6002	6001	<input type="checkbox"/>	<input type="checkbox"/> S
6027	6018	<input type="checkbox"/>	<input type="checkbox"/> S
6028	6005	<input type="checkbox"/>	<input type="checkbox"/> S
6036	-	<input type="checkbox"/>	<input type="checkbox"/> S
6037	-	<input type="checkbox"/>	<input type="checkbox"/> S
6038	-	<input type="checkbox"/>	<input type="checkbox"/> S
6039	-	<input type="checkbox"/>	<input type="checkbox"/> S
7001	-	<input type="checkbox"/>	<input type="checkbox"/> S
7002	7035	<input type="checkbox"/>	<input type="checkbox"/> S
7003	-	<input type="checkbox"/>	<input type="checkbox"/> S
7024	-	<input type="checkbox"/>	<input type="checkbox"/> S
7060	-	<input type="checkbox"/>	<input type="checkbox"/> S
7071	-	<input type="checkbox"/>	<input type="checkbox"/> S
7179	-	<input type="checkbox"/>	<input type="checkbox"/> S
7244	7043	<input type="checkbox"/>	<input type="checkbox"/> S
SILVER 7500	9006	<input type="checkbox"/>	<input type="checkbox"/> S
7999	-	<input type="checkbox"/>	<input type="checkbox"/> S
8020	8017	<input type="checkbox"/>	<input type="checkbox"/> S
9002	-	<input type="checkbox"/>	<input type="checkbox"/> S
9013	9010	<input type="checkbox"/>	<input type="checkbox"/> S
(New) P6058/9917	-	<input type="checkbox"/>	<input type="checkbox"/> S
P6808/9917	-	<input type="checkbox"/>	<input type="checkbox"/> S

700
g/m²

1 Side
Printable

Dull

Weldable

REACH
Compliant

SIOEN



TRUCK TILT MEDIUM^{TOP}

Product code: P9701

Fabric	100 % PES 1100 dtex		
Weight	700 g/m ²	DIN EN ISO 2286-2	
Breaking strength	Warp	3000 N/ 5 cm	EN ISO 1421-1
	Weft	2800 N/ 5 cm	
Tear strength	Warp	300 N	DIN 53 363
	Weft	300 N	
Adhesion	90 N/ 5 cm	EN ISO 2411	
Temperature resistance	-30/ + 70 °C	DIN EN 1876-2	
Application	Truck tilt		
Width	300 cm		
Color	9038		

Outdoor

• Solvent • Eco-Solvent • Mild-Solvent • Latex • UV curable •

TILTS • B9000

LIST OF PROPERTIES

		B9000
MATERIAL COMPOSITION		
FABRIC		100 % PES / 1100 DTEX
TOTAL WEIGHT	DIN EN ISO 2286/2 1998	680 G/M ²
LACQUERING		1/1
EMBOSSING		GLOSSY
BREAKING STRENGTH WARP	EN ISO 1421/1 1998	3000 N / 5 CM
BREAKING STRENGTH WEFT	EN ISO 1421/1 1998	2800 N / 5 CM
TEAR STRENGTH WARP	DIN 53363 2003	300 N
TEAR STRENGTH WEFT	DIN 53363 2003	300 N
ADHESION	EN ISO 2411 2000	100 N / 5 CM
TEMPERATURE RESISTANCE	DIN EN 1876/2 1998	-30/+70 °C
LIGHT FASTNESS (EXCEPT WHITE AND (HALF-)TRANSPARENT)	ISO 105 B02 1988	7 - 8
FIRE BEHAVIOR	ISO 3795 1989	< 100 MM/MIN
APPLICATION		TRUCK / TILT

All our technical characteristics are indicative

SIDE CURTAINS • P6825

LIST OF PROPERTIES

		P6825
MATERIAL COMPOSITION		
FABRIC		100 % PES / 1100 DTEX
TOTAL WEIGHT	DIN EN ISO 2286/2 1998	900 G/M ²
LACQUERING		1/1
EMBOSSING		GLOSSY
BREAKING STRENGTH WARP	EN ISO 1421/1 1998	4000 N / 5 CM
BREAKING STRENGTH WEFT	EN ISO 1421/1 1998	4000 N / 5 CM
TEAR STRENGTH WARP	DIN 53363 2003	600 N
TEAR STRENGTH WEFT	DIN 53363 2003	500 N
ADHESION	EN ISO 2411 2000	100 N / 5 CM
TEMPERATURE RESISTANCE	DIN EN 1876/2 1198	-30/+70 °C
LIGHT FASTNESS (EXCEPT WHITE AND (HALF-)TRANSPARENT)	ISO 105 802 1988	7 - 8
FIRE BEHAVIOR	ISO 3795 1989	< 100 MM/MIN
APPLICATION		TRUCK/SIDECURTAIN

All our technical characteristics are indicative

9917 – 300 CM - NOT PRINTED ©

				
100 % PES 1100 DTEX	900 G/M ²	WA: 4000 N / 5 CM - 600 N WE: 4000 N / 5 CM - 500 N	-30/+70 °C LIGHT FASTNESS 7 - 8	< 100 MM/MIN

© THIS IS A STANDARD PRODUCT.





B9680 TEKNİK ÖZELLİKLER

Kumaş Yapısı	100% PES	1100 dtex	
Ağırlık	660 g/m ²	DIN EN ISO 2286 - 2	1998
Lak	1/1		
Yüzey	Parlak		

Kopma Mukavemeti

Çözü	2500 N/5 cm	EN ISO 1421	1998
		meth 1	
Atkı	2300 N/5 cm		

Yırtılma Mukavemeti


Çözü	270 N	DIN 53 363	1969
Atkı	270 N		

Yapışma	90 N/5cm	EN ISO 2411	2000
Isıl Dayanım	-30 °C/+70 °C	DIN EN 1876 - 2	1998
Işık Haslıđı	7-8	ISO 105 B02	1988
Yanmaya Karşı Mukavemet	<100 mm/dk	ISO 3795	1989

B7672

Fabric / Weefsel / Tissu / Gewebe / Tejido	100 % PES / 1100 dtex	
Total weight / Gewicht totaal / Poids total / Totalgewicht / Peso total	680 g/m ²	DIN EN ISO 2286/2 1998
Lacquering / Vernis / Lackierung / Lacado	1/1	
Embossing / Kalander / Calandre / Lackierung / Embossing	Glossy	
Breaking strength Warp Treksterkte Ketting Résistance rupture Chaîne Höchstzugkraft Kette Resistencia a la ruptura Urdimbre	2500 N/5cm	EN ISO 1421/1 1998
Breaking strength Weft Treksterkte Inslag Résistance rupture Trame Höchstzugkraft Schuss Resistencia a la ruptura Trama	2000 N/5cm	EN ISO 1421/1 1998
Tear strength Warp Scheurweerstand Ketting Résistance à la déchirure Chaîne Weiterreisskraft Kette Resistencia a la rasgadura Urdimbre	270 N	DIN 53363 2003
Tear strength Weft Scheurweerstand Inslag Résistance à la déchirure Trame Weiterreisskraft Schuss Resistencia a la rasgadura Trama	270 N	DIN 53363 2003
Adhesion / Hechting / Adhérence / Haftung / Adherencia	90 N/5cm	EN ISO 2411 2000
Temperature resistance / Temperatuursbestendigheid / Tenue à la température / Temperatuursbeständigkeit / Résistencia à la temperatura	-30/+70 °C	DIN EN 1876/2 1998
Light fastness (Except white and (half-)transparent) Lichtechtheid (Uitgezonderd wit en (half-)transparent) Tenue à la lumière (Excepté en blanc et (semi-)transparent) Lichtechtheit (Ausnahme weiss und (semi-)transparent) Resistencia a la luz (Excepto blanco / (semi-)transparente)	7-8	ISO 105 B02 1988
Fire behavior / Brandgedrag / Reaction au feu / Brennverhalten / Fire behavior	< 100 mm/min	ISO 3795 1989
Application Truck/Roof/Regular		

TRUCK



SIOEN INDUSTRIES

SIDE CURTAINS
B6000 • P6819 • P6825

SIOEN

B 9000

SIOEN

Fabriekstraat 23
B-8850 Ardooie
Belgium
Tel. +32 51 74 09 00
info@sioen.com

Get social:



www.sioen.com

SIOEN

SICEM

